

**HM Wire International, Inc.**  
**Ph: 330-244-8501 Fax: 330-244-8561**  
**www.litz-wire.com info@litz-wire.com www.hmwire.com**



## Characteristics Comparison of CCA

Characteristic	CCA Wire	Copper Wire	Aluminum Wire
Copper Volume	5	100	0
Gravity	3.63	8.89	2.7
Length Comparison With Copper	2.5:1	1:1 3	.29:1
Conductivity	70	100	62
DC Resistivity	0.02462	0.01724	0.0274
Tensile Strength (N/mm2)	95 - 135	215 - 265	69 - 107
Elongation (%)	≥ 10	≥ 20	≥ 8
Windability	Good	Very Good	Good
Weight	Good	Bad	Very Good
Soldering	Very Good	Very Good	Bad
DC Resistance	Good	Very Good	Good

\*To be used as a guideline only

Copyright © HM Wire International Inc. 2011

R1. 9/20/2011