

HM Wire International, Inc.

Ph: 330-244-8501 Fax: 330-244-8561

www.litz-wire.com info@litz-wire.com www.hmwire.com

Fluorinated Ethylene Propylene (FEP), Molded/Extruded

| Optical Properties | Metric | English |
|-----------------------|---------------|---------------|
| Transmission, Visible | 92.0 - 95.0 % | 92.0 - 95.0 % |
| IR Transmittance | 95.0 - 98.0 % | 95.0 - 98.0 % |
| UV Transmittance | 91.0 - 92.0 % | 91.0 - 92.0 % |

Some of the values displayed may have been converted from their original units and/or rounded in order to display the information in a consistent format. To be used as a guideline only. TEFLON® is a registered trademark of DuPont.

Copyright HM Wire International 2009

Rev 1.11032009